

PINK DISSIPATIVE PE FOAM EAR



Product Specifications

Property	Test Method	Unit	Value
Density	ASTM D3575-08 Suffix W ISO 845:2006	Kg/m ³	37
Compressive Strength	ISO-3386-1		
25 %		kPa	55
40 %		kPa	85
50 %		kPa	120
Compression set	ISO-1856-C		
0.5h		%	14
24h		%	10
Tensile Strength at Break	ISO-1926	kPa	335
Tensile Elongation	ISO-1926	%	88
Thermal stability	Internal		100°C <5%
Shore A	ISO 868-1985		11
Shore 0	ASTM D2240		19
Shore 00			55
Surface resistance	DIN 61340-2-3	kOhm	< 100
Volume resistivity		kOhm/cm	< 100

Part Number and Features

Part Number	Features
83-500-xxxx	Standard Sheet - 1375 x 1200 mm
26-5xx-xxxx	Foam customized settings