

GLOW CORE NO CLEAN CORED WIRE SOLDER

FEATURES

- Fast Wetting with Pb-Free Alloys
- Pleasant Odor
- Clear Residue
- Extends Solder Tip Life
- ROL0 per IPC J-Std-004
- REACH and RoHS Compliant*
- Passes BONO Testing



Glow Core is a no-clean cored wire solder designed to offer excellent wetting characteristics with both leaded and lead-free alloys. The novel activator in Glow Core produces fast cycle time and powerful capillary action. Glow Core promotes thermal transfer, offering better solder penetration into plated through holes or surface mount interconnections. Glow Core cored wire produces low-to-medium post-process residues that are electrically safe that do not require cleaning.

STANDARD AVAILABILITY

Glow Core is available in Sn/Pb, Sn/Cu, SAC, SN100 C^{\otimes} , REL61TM and REL22TM alloys. Other alloys, diameters and spool sizes may be available upon request.

Diameter	Spool Size	Case Weight
.010	½ lb.	12 lb.
.015	½ lb.	12 lb.
.020	1 lb.	24 lb.
.032	1 lb.	24 lb.
.062	1 lb.	24 lb.

^{*}Lead-free



APPLICATION

Best results are obtained with solder iron tip temperature between 300° - 400° C (575° - 750° F) for leaded alloys and 370° - 425° C (700° - 800° F) for lead-free and SN100C[®] alloys. If additional flux is required AIM NC280 flux is recommended.

HANDLING & STORAGE

Time	Parameters
Indefinite	Proper storage conditions

Store cored wire in a clean, dry area away from moisture and sunlight. Do not freeze this product.

CLEANING

Glow Core can be cleaned with saponified wash and many commercially available flux removers. Contact AIM for specific information.

SAFETY

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

Document Rev # NF12 Page 1 of 1

DISCLAIMER The information contained herein is based on data considered accurate and is offered at no charge. Product information is based upon the assumption of proper handling and operating conditions. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please refer to http://www.aimsolder.com/terms-conditions to review AIM's terms and conditions.