

HumiSeal[®] Stripper 1100 Technical Data Sheet

HumiSeal[®] Stripper 1100 is a unique stripper to remove dual cure acrylated urethane conformal coating such as UV40 family products. HumiSeal[®] Stripper 1100 does not contain any halogenated hydrocarbons, aromatics or flammable ingredients. Unlike methylene chloride based products that evaporated quickly, HumiSeal[®] Stripper 1100 remains on the surface to penetrate and soften the coating. HumiSeal[®] Stripper 1100 will not remove or attack solder, copper, silver, gold and nickel plating. HumiSeal[®] Stripper 1100 is in full compliance with the RoHS Directive (Directive 2002/95/EC).

Typical Physical Properties of HumiSeal[®] Stripper 1100

Stripper	1100
Compatible HumiSeal [®] Coatings	UV40, UV40-250, UV40HV, and UV40 GEL Products
Relative Evaporating Rate (BuAc=1)	< 1.0
Specific Gravity	1.05
Flash Point (°C) TCC	92.8
VOC (grams/litre)	1,049
Shelf Life, DOM	36 months
Color	Light Amber to Clear

Directions for Use

Immerse the component or printed circuit board assembly into HumiSeal[®] Stripper 1100. The rate at which the existing coating will dissolve will depend upon its thickness and age. Most coatings of normal thickness will normally be completely removed in approximately up to 30 minutes or less. The use of mechanical mixers will speed up the dissolving rate. HumiSeal[®] Stripper 1100 can also be used to remove coating from small areas, by applying a few drops to the desired location.

After the existing coating has been removed, thoroughly wash the assembly in isopropyl alcohol, deionized water or other qualified cleaning process. If the component surface of is cloudy after washing, the removal is incomplete. The removal should be repeated for a longer time. Oven dry the assembly for a minimum of 30 minutes at 66°C prior to recoating.

Handling Precautions

HumiSeal[®] Stripper 1100 contains powerful and non-hazardous solvents, however the following standard safety precautions should be observed:

- Use only in well ventilated areas.
- Protective gloves and goggles should be worn.
- In case of prolonged skin contact, wash with water.
- In case of eye contact, flush with water and contact physician.
- Avoid prolonged breathing of vapors.

- Unused portions of HumiSeal[®] products must be disposed of in compliance with applicable environmental regulations.
- Consult the Material Safety Data Sheet (MSDS/SDS) for more specific product information.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrières-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.